





Material: Nylon Type 6 Heat Stabilized


Chemlon 212 H

Chem Polymer Corporation / Nylon 6 Heat Stabilized

Nylon Type 6 heat stabilized has the same mechanical properties as general purpose nylon 6/6 with the additional advantage of heat stabilization. This material can withstand 250°F (121°C) temperature in long range service in most applications. Heat stabilized nylon is off white in colour.







E

Description			Mounting Hole			Bushings		
Cross Section	Cable Size	Cable Type	Gauge (AWG)	Diameter A	Flats B	Max. Panel Th. C	Length D	Width E
	0.3 (7.2)	SJT	16/2	0.625		0.062 (1.6)	0.74 (18.8)	0.64 (16.2)
Round	0.355 (9)	SJ	16/3	(15.9)	0.55 (14)			
	0.405 (10.2)	SJT	18/3	0.625 (15.9)				

Dimensions : Inches (Millimetres)

Part Number Table

Description	Part Number	
Strain Relief Bushing, Nylon	23MP06N34EZ	

Important Notice : This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselved to be accurate out the Group assumes to responsibility of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp is the registered trademark of the Group. © Premier Farnell plc 2012.

www.element14.com www.farnell.com www.newark.com

