
## Miniature Case

## **BC2** Series








# Miniature Case

## **BC2 Series**





#### Dimensions : Millimetres

### ABS Polymers Specification Acrylonitrile-Butadiene-Styrene

Properties	Test Method	11-14	Impact Resistant Grades	
		Unit	103	
Izod Impact Strength +23°C -20°C	ISO 180/3A ASTM D256/A	kJ / m <sup>2</sup>	17 11	
Tensile Strength at Yield	ISO R527 ASTM D638 N / mm <sup>2</sup>		50	
Elongation at Yield	ISO R527 ASTM D638	%	6	
Flexural Strength	ISO 178 ASTM D790	N / mm <sup>2</sup>	87	
Rockwell Hardness	ISO 2039/2 ASTM D785	R Scale	112	
Heat Deflection Temperature Unannealed Annealed	ISO 75/A ASTM D648	°C	90 97	
Vicat Softening Temperature ISO 306/B ASTM D1525		°C	97	

www.element14.com www.farnell.com www.newark.com




# Miniature Case



## **BC2** Series

Properties	Test Method	Unit	Impact Resistant Grades	
		om	103	
Density	ISO R1183 ASTM D792/A	kg / m <sup>3</sup>	1,050	
Melt Flow Index	ISO 1133 ASTM D1238	dg / min	13	



**Dimensions : Millimetres** 

### **Specification Table**

Colour		Part Number				
Colour	Length (L)	Width (W)	Height (H)	Maximum PCB Size		
Black					BC2	
Grey (RAL9002)		62	23	64 × 56	BC2LG	
White					BC2W	

**Dimensions : Millimetres** 

Important Notice : This data sheet and its contents (the "Information") belong to the members of the Premier Famell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Multicomp is the registered trademark of the Group. © Premier Farnell plc 2012.



www.element14.com www.farnell.com www.newark.com