1-800-383-7323 USA/CAN www.energizer.com

EVEREADY 763



Industry Standard Dimensions

mm (inches)

Chemical System: Zinc-Manganese Dioxide (Zn/Mn02)

ANSI / NEDA-710 Designation: **Battery Voltage:** 22.5 Volts

Average Weight: 372 grams (13.2 oz.)

Volume: 311 cubic centimeters (19.0 cubic inch)


1,700 mAh to 0.8 volts/cell **Average Capacity:**

(Rated at 25 mA continuous drain at 21°C)

Cells: Forty Five No. 130


Three parallel strings of fifteen in series

Jacket: Paper



TYPICAL DISCHARGE CURVE

Simulated Test @ 21°C (70°F)



Simulated Application Test Estimated Average Service at 21°C (70°F)

	Typical Drains		Cutoff Voltage
Schedule:	at 18V (milliamperes)	Load (ohms)	12V 13.5V 15V 16.5V 18V 19.5V
			Hours
24 hours/day	3.6	5,000	491 435 347 227
4 hours/day	14.4	1,250	135 125 112 92 75 46

Important Notice

This data sheet contains information specific to batteries manufactured at the time of its publication. Contents herein do not constitute a warranty. Copyright © Eveready Battery Co. Inc. - All Rights Reserved

Form No. EBC - 3233D Page 1 of 1