




Material Datasheet

03.04.2023

TLFX48YE
Article Number 554-51201



Material: Polyolefin, cross-linked (PO-X)
Colour: Yellow (YE)

Supplied \varnothing D min.: 4.8 mm
Recov. \varnothing d max.: 2.4 mm
Wall (WT): 0.61 mm
Shrink Ratio: 2:1
Min. Shrink Temperature - °C: +70 °C

Operating Temperature : -55 °C to +125 °C

Tensile Strength: 12 MPa
Elongation at break: 4.5
Longitudinal Change After Shrinkage: -6%

Test Method

ASTM D2671
ASTM D2671

We assume no responsibility that the Product will be used for the intended purpose, this is beyond our control. It's up to the customer to check the suitability for a specific application by means of tests. Technical changes and errors reserved



Material Datasheet

03.04.2023

Oxygen index: 32.5 %

Print Method: Thermal transfer print

Print Method (Alternative): Laser beam print

Application Tool: H6100, TT431, TT4030, TrakMark DS

HF ✓ LFH ✓ RoHS ✓ **EN 45545-2**

We assume no responsibility that the Product will be used for the intended purpose, this is beyond our control. It's up to the customer to check the suitability for a specific application by means of tests. Technical changes and errors reserved